**Qingdao Casting Quality Industrial Co., Ltd** 

# Abrasion-Resistant Cast Iron 15% Cr-Mo

15% Cr-Mo is a popular abrasion resistant cast iron in ASTM A532 standard; it is one type of White Iron.

## **Casting Methods in Casting Quality Industrial**:

- Sand Casting
- Shell Casting

### **Equivalent Abrasion-Resistant Cast Iron Grade:**

EN 12513 Grade EN-GJN-HB555(XCr14) EN5.5608 DIN 1695 Grade G-X 300 CrMo 15 3 (DIN 0.9635) DIN 1695 Grade G-X 300 CrMoNi 15 2 1(DIN 0.9640)

## **Reference Casting Standards:**

ASTM A532 Standard Specification for Abrasion-Resistant Cast Irons

ASTM A532 Class II type B 15% Cr-Mo chemistry requirement: www.castingquality.com

Standard	ASTM A532
Class	II
Туре	В
Designation	15% Cr-Mo
Carbon %	2.0-3.3
Manganese %	2.0 max
Silicon %	1.5 max
Nickel %	2.5 max
Chromium %	14.0-18.0
Molybdenum %	3.0 max
Copper %	1.0 max
Phosphorus %	0.10 max
Sulfur %	0.06 max



## ASTM A532 Class II type B 15% Cr-Mo Mechanical Property:

No requirement about tensile/yield and elongation. www.castingquality.com

# ASTM A532 Class II type B 15% Cr-Mo Hardness Requirements:

Standard	ASTM A532
Class	II



# **Material Data Sheet**

# **Qingdao Casting Quality Industrial Co., Ltd**

Туре	В	
Designation	15% Cr-Mo	
As Cast or As cast	450HB/46HCR/485HV	
and Stress relieved		
Hardened or	Level 1	600HB/56HRC/660HV
Hardened and	Level 2	650HB/59HRC/715HV
Stress Relieved		
Chill Cast, min	-	
Softened, max	400HB/41HRC/430HV	

ww.castingquality.com

# ASTM A532 Class II type B 15% Cr-Mo Heat treatment process

It will be up to the hardness requirement: as Cast, as Cast and Stress relieved, Hardened, Hardened and stress relieved, Softened for machining.

# ASTM A532 Class II type B 15% Cr-Mo Typical Casting Application:

- Pump industry.
- Mining industry, crusher liner, chute liner.
- Oil or recycling.

#### What is White Iron?

When white iron solidifies, virtually all the carbon appears in the form of carbides, White irons are hard and brittle, and they break with a white fracture. These irons are usually alloyed with Chromium and Nickel. The hardness is in the range of 500 to 600 BHN, the specific alloying that is required in a function of section size and application; there must be coordination between designer and foundry. These irons exhibit outstanding wear resistance and are used extensively in the mining industry for ball mill shell liners, balls, impellers, and slurry pumps. www.castingquality.com